

Protective-film base film

Base Film for Adhesive-Coated Masking Film

Base Film for Adhesive-Coated Masking Film

TECHNICAL DATA

(The below are representative/measured values and not guaranteed values.)

Features

Base film for adhesive-coated masking film that can be used for a variety of protective films.

- Excellent mold release for untreated surfaces.
- Few cosmetic defects (low fisheye).
- Manufactured on a production line with a proven track record in optical applications.

	Base Film for Adhesive-Coated Masking Film	
Product and Type	TORAYFAN™ NO 40_3701J	TORETEC™ 50_CF470
Tensile Strength MD (MPa)	65	35
Tensile Strength TD (MPa)	40	25
Tensile Elongation MD (%)	700	650
Tensile Elongation TD (%)	800	800
Young's Modulus MD (MPa)	700	300
Young's Modulus TD (MPa)	650	250
Haze (%)	25	14
Wetting Tension (dyn/cm)	36	38
Features	Non-oriented polypropylene film	Non-oriented polyethylene film

OVOL Nihonbashi Bldg 6F, 3-4-4 Nihonbashi Muromachi, Chuo-ku, Tokyo 103-0022 Tel : 81-3-5200-5635

Fax: 81-3-5200-5622